



## VOC EMISSIONS TEST SUMMARY

January 2010

Supplier : Rephouse

Flooring: Neoflex™ 500, 600, 700, 800, Natural and Reco Series  
Rubber Flooring

Test Method:

Carpet & Rub Institute Green Label Test Program Incorporating  
ASTM D 5116 "Standard Guide for Small-Scale Environmental  
Chamber Determinations of Organic Emissions from Indoor  
Materials/Products".

Emission

Data:

Chemical Species	Specific Area Emission Rate mg/m <sup>2</sup> /hr
Total Volatile Organic Compounds	0.3mg/m <sup>2</sup> /hr (24 hours)
Formaldehyde	0.02mg/m <sup>2</sup> /hr (24 hours)
4-Phenylcyclohexene	<0.01mg/m <sup>2</sup> /hr (24 hours)
Styrene	<0.01mg/m <sup>2</sup> /hr (24 hours)
Ethylene Glycol	0.01mg/m <sup>2</sup> /hr (24 hours)
Polyester Polyol	<0.01mg/m <sup>2</sup> /hr (24 hours)
Aluminium Hydroxide	<0.01mg/m <sup>2</sup> /hr (24 hours)
Antimony Trioxide	<0.01mg/m <sup>2</sup> /hr (24 hours)
Microcrystalline Silica	<0.01mg/m <sup>2</sup> /hr (24 hours)

© Rephouse